



TECHNICAL DATA SHEET No 130

P962 1K ISOLATOR

GENERAL TECHNICAL DESCRIPTION

1K air-drying isolator primer based on natural components.

Prevents the lifting and isolates the old, existing paint films, which are sensitive to strong solvents.

Fast drying properties.

Does not require sanding after application.

SURFACE

Any coated surface

PRETREATMENT/CLEANING OF SUBSTRATE

The surface to be coated must be dry, clean, and free of grease and other contaminants. Ensure all substrates are thoroughly cleaned and dried at every step of the preparation process.



Clean the surface with 770 NORMAL / 771 FAST ANTISIL Degreaser.

Use 2 clothes wipe on, wipe off. Always wipe cleaner off the surface as long is wet, with a clean, dry cloth.

Remove dust by air blowing and a tack cloth.



P 180 / P 220

or



P 400, Sanding by hand, wet

PRODUCT APPLICATION: Apply 1 - 2 thin coats.



Stir well before using



No thinner / reducer required



Ready to spray: 20 - 25 s
DIN 4 / 20°C (68°F)



1.5 – 1.8 mm
1.7 - 2.2 bar (25 - 32 psi)
1 - 2x coats = 20 - 40 µm
(0.8 - 1.6 mil)



5 - 10 min / 23°C (73°F)
Flash off time between coats



1 h / 23°C (73°F)
Non force dry



It can be overcoated with any HB BODY 1K / 2K primer or 260 BODYFILLER.

SPECIFIC GRAVITY

1 ± 0.05 g/cm³

SOLID CONTENT

45 ± 2% Weight

VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 540g/L.

2004/42/IIIB(c)(540)540

THEORETICAL COVERAGE

12 - 15 m² / l at 20 µm (0.8 mil) dry film thickness

CLEANING OF EQUIPMENT

Clean after final use with T769 GUN WASH CLEANER

REMARKS

- Make sure you stir well and filter the product before every use.
- Do not exceed the thickness mentioned above during application.
- Optimum operating temperature range 10 - 30°C (50 - 86°F).

STORAGE SHELF LIFE

Guaranteed shelf life of 18 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective equipment



Follow the application instructions mentioned in this TDS

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

SEPTEMBER 2024